


Your Replacement Battery Source

Rechargeable Sealed Lead Acid Battery

BC-682

(6V 9.0Ah/20hr)








These rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

Application

- · Alarm System
- · Cable Television
- · Communication Equipment
- · Control Equipment
- · Security System
- · Medical Equipment
- · UPS
- · Power tools
- · Emergency Power System
- · Toys







Battery Construction									
Component Positive plate Negative plate Container Cover Safety valve Terminal Separator E								Electrolyte	
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid	


General Features

- Absorbent Glass Mat(AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transportcomplies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.


Performance Characteristics								
Designed Floating Life	5 Years							
Capacity (25°C)	20HR(0.45A,1.75V)	10HR(0.86A,1.75V)	5HR(1.52A,1.75V)	1HR(5.85A,1.75V)				
Capacity (25 C)	9AH	8.6AH	7.6AH	5.85AH				
Dimensions	Length	Width	Height	Total Height				
Difficitsions	98mm(3.86inch)	57mm(2.24inch)	115mm(4.53inch)	115mm(4.53inch)				
Approx. Weight	3.00lbs							
Internal Resistance	Full charged at 25°C: 0.012 Ohm							
Self Discharge	3% of capacity declined per month at (25°C)							
Capacity Affected	40°C	25°C	0°C	-15°C				
by Temp. (20HR)	102%	100%	85%	65%				
Charge Voltage	Cycle	e use	Float use					
(25°C)	7.2-7.5V(- max. Curi		6.8-6.9V(-10mV/°C)					




Charge characteristic




Discharge characteristic (25°C)



Relationship of OCV and state of charge



Cycle service life



CITY (%) NUMBER OF CYCLES

Constant current discharge ratings-amperes at 77°F 25°C									
F.V/Tim e	5 min	10 min	15 min	30 min	1HR	3HR	5HR	10HR	20HR
1.60V	35.2	21.9	16.5	10.1	6.40	2.81	1.72	0.96	0.51
1.67V	33.0	20.8	15.9	9.63	6.31	2.70	1.68	0.95	0.49
1.70V	30.2	20.0	15.5	8.75	6.12	2.52	1.64	0.95	0.48
1.75V	29.6	19.4	15.0	8.31	5.83	2.44	1.61	0.93	0.47
1.80V	26.5	18.5	13.6	7.70	5.46	2.34	1.51	0.92	0.45
1.85V	23.4	17.6	12.3	7.09	5.09	2.26	1.42	0.91	0.44

Constant power discharge ratings-watts at 77°F 25°C										
F.V/Time	5 min	10 min	15 min	30 min	1HR	3HR	5HR	10HR	20HR	
1.60V	61.7	39.5	30.1	18.1	11.5	4.98	2.90	1.92	1.01	
1.67V	59.5	38.5	29.8	17.8	11.5	4.82	2.89	1.91	0.97	
1.70V	56.0	38.1	29.5	16.6	11.3	4.61	2.85	1.90	0.96	
1.75V	56.4	38.0	29.3	16.1	11.1	4.50	2.83	1.87	0.94	
1.80V	51.6	37.4	27.1	15.4	10.4	4.37	2.74	1.85	0.91	
1.85V	46.8	35.5	24.6	14.4	9.8	4.24	2.65	1.82	0.88	